

TECHNICAL DATA SHEET

NPR-5300 SERIES EPOXIES

Structural Epoxy System for Infrastructure Protection

Rev. 20251215



DESCRIPTION

Neopoxy NPR-5300 Series Epoxies are two-part 100% solids structural epoxy coatings with exceptional chemical resistance and adhesion to a variety of surfaces including concrete and steel. High build formulation allows NPR-5300 Epoxies to be hand applied at up to 500 mils or spray applied at up to 300 mils in a single pass. Cures rapidly to allow the application area to go back into service within one hour. Third party testing and decades of field experience demonstrate excellent chemical resistance to sulfuric acid, nitric acid, sodium hydroxide, hydrogen sulfide, caustics, gasoline, and other hydrocarbons. NPR-5300 Epoxies come in five different viscosities to meet the needs of any municipal or private project.

FEATURES

- 100% solids, solvent free, no VOCs
- Chemical and corrosion resistant
- Very strong surface bond
- Prevents inflow and infiltration
- Protects for decades
- Structural coating
- Verified by independent testing
- On the market since 1999
- Available in five different viscosities

USES

- Protection of new or corroded concrete and steel infrastructure, including manholes, sumps, wet wells, pipelines, vaults, tanks, concrete surfaces, cracks, WTPs, and more
- End sealing or patching for CIPP liners
- PVC coating and bridging with other materials (requires primer coat with Neopoxy NPR-3200 PVC Adhesive)

VISCOSITY OPTIONS

Product*	Viscosity	Application Method	Maximum Single Coat Thickness
NPR-5301	Super Low	Spray or Hand Application	40 mils
NPR-5302	Low	Spray or Hand Application	70 mils
NPR-5303	Medium	Spray or Hand Application	150 mils
NPR-5304	High	Spray or Hand Application	300 mils
NPR-5305	Super High	Hand Application	500 mils

*All products above have identical physical properties. Consult with Neopoxy representative to determine which viscosity is most suitable for your application.

PACKAGING OPTIONS

- 8.5 Gallon Set (Hand Application), 5 55-Gallon Drum Set (Spray Application)
- Additional sizes available in One-Step Kits and Sets (see separate TDS): .5 gal, 1 gal, 1.5 gal, 3 gal

PHYSICAL PROPERTIES

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Description	Standard	Data
Mix Ratio (Resin/Hardener)	-	1.5 to 1 by Volume 1 to 1 by Weight
Initial Cure Time, 100 Grams @ 77°F (25°C)	-	30 Minutes
Pot Life, 100 Grams @ 77°F (25°C)	-	20 Minutes
Appearance	-	Resin (Part A): Green Hardener (Part B): White Mixture: Light Green
Weight Per Gallon (Resin)	-	8.9 – 9.1 lbs.
Weight Per Gallon (Hardener)	-	13.9 – 14.3 lbs.
Weight Per Gallon (Mixture)	-	10.9 – 11.2 lbs.
Specific Gravity (Resin)	-	1.06 – 1.09 G/ml
Specific Gravity (Hardener)	-	1.64 – 1.71 G/ml
Maximum Service Temp. (Ambient Cure)	-	150°F (66°C)
Maximum Service Temp. (Postcured)	-	168°F (76°C)
Coefficient of Linear Thermal Expansion	-	37×10^{-6} cm/cm/°C
Shrinkage	-	<0.5%
Flexural Strength	ASTM D-790	15,000 psi
Flexural Modulus	ASTM D-790	600,000 psi
Tensile Strength	ASTM D-638	7,500 psi
Tensile Modulus	ASTM D-638	290,000 psi
Tensile Elongation	ASTM D-638	5%
Compressive Strength	ASTM D-695	20,000 psi
Shore D Hardness	ASTM D-2240	>86
Adhesion to Concrete	ASTM D-4541 ASTM D-7234	Concrete Failure
Adhesion to Steel	ASTM D-4541	>2,500 psi
Abrasion Resistance (Taber Abraser)	ASTM D-4060	50 mg loss (1000 cycles @ 1000 gram load)
Volatile Organic Compounds (VOCs)	ASTM D-3960	0.0 lbs./Gallon
Chemical Resistance	ASTM F-1216 ASTM D-543 ASTM D-2122	Requirements Met

DIRECTIONS FOR USE

SURFACE PREPARATION: Any concrete surface must be fully cured prior to coating (typically 28 days for Portland cement). All inflow and infiltration must be stopped prior to application. High pressure wash all surfaces to be coated at minimum 4000 PSI in order to remove contaminants, paint, laitance, etc. After power washing, remove standing water and blow warm air on surface until visibly dry. There should be no darkened areas, as this may indicate surface moisture. For confirmation of surface dryness, applicant may choose to do the "Plastic Sheet Method" test detailed in ASTM D4263. Surface pH should be between 6-10. The product can be applied to any concrete surface profile, CSP 1 to CSP 10 (the rougher the surface the stronger the adhesion). Steel surfaces to be coated should be prepared according to SSPC-SP 10/NACE No. 2 "Near White Blast Cleaning". Steel surfaces may also require following SSPC-SP-1 (Solvent Cleaning) to remove any soluble contaminants.

APPLICATION CONDITIONS: The temperature of the air and surface to be coated should be between 40-80°F during application. It is important to apply the product while the temperature is either stable or falling. Relative humidity must be below 80%.

MIXING & HAND APPLICATION: Product must be mixed according to the Mix Ratio shown in the Physical Properties table in this document. Mix product in bucket with paint stick or right angle ½" drill (such as Milwaukee Super Hawg) with paint mixing paddle until there is no streaking and color is a consistent light green. When mixing, make sure to scrape the sides and reach all the way to the bottom of the bucket. Using a paint trowel or putty knife, remove mixed epoxy from the bucket as rapidly as practical and safe. Spread the epoxy directly onto the surface to be protected.

SPRAY APPLICATION: Specialized high pressure plural component spray equipment is required for spray application (i.e. Graco XP-50). Please consult with Neopoxy representative if interested in spray application.

CLEAN UP: Clean any surface spills or overspray as quickly as possible with isopropyl alcohol or acetone. For cleaning skin, first wipe off epoxy with soft rag and then wash area with soap and warm water.

SHELF LIFE & STORAGE: Store product in closed container at 40°-80°F. Shelf life is one year from the manufacture date indicated on label.

SAFETY: Use of safety goggles, particle masks, coveralls, and chemical resistant gloves is recommended. Work in a clean, well-organized area with adequate ventilation. Keep uncured product containers tightly closed and away from children at all times. Please read and understand the full safety recommendations as set forth in the Safety Data Sheets (SDS) available on our website.

ADDITIONAL PRODUCT INFORMATION

COATING THICKNESS: Refer to Viscosity Options chart to determine maximum coating thickness. Exceeding the listed maximum coating thickness may result in sagging. While every project and surface is different, it is considered “standard” to apply 125 mils to new concrete infrastructure and 250 mils to corroded concrete infrastructure. Please consult with Neopoxy representative to determine the best thickness for your project. Since this is a 100% solids solvent-free product, there is minimal shrinkage. Wet and dry-film thicknesses are equal.

COVERAGE: One gallon covers 12 square feet at 1/8” thickness (125 mils).

CURE TIME: Epoxy is “temperature sensitive,” meaning that it will cure faster at higher temperatures. Epoxy is also “mass sensitive,” meaning that the larger the volume, the shorter the working time. For example, when applied onto a surface at 1/4” thickness, the product will harden in approximately one hour. However, when applied at thickness of 1/2”, the time to harden may be as little as 30 minutes. **It is important to limit the mass of mixed epoxy by continuing to mix it or by spreading it to extend the working time.**

ENVIRONMENTAL: Neopoxy epoxies are comprised entirely of reactive solids (resin & hardener), which means that there are no solvents or thinners that evaporate during the curing process. Since the curing process binds all reactive components, the cured epoxies are inert, non-leeching, and safe for use on stormwater infrastructure, wastewater infrastructure, or for discharge into a wastewater treatment facility or natural body of water. Prior to mixing the epoxy, the applicant must handle the uncured resin and hardener with care and clean up any spills in accordance with local environmental regulations. For additional information please reference Safety Data Sheets (SDS) available on our website.

RECOAT WINDOW: Multiple layers may be applied to build thickness, but the materials must be allowed to cure and become cool to the touch before applying the next layer. Recoat window may be extended up to several months as long as the surface is clean and free of contaminants and amine blush.

THINNING: To lower viscosity, place containers in heated room or submerge bottom of container in hot tap water. For plural component spray application, drum heaters or inline heaters may be used. **Do not thin with solvents.**

WARRANTY & DISCLAIMER: Neopoxy LLC (“Neopoxy”) warrants its products to be free of manufacturing defects in accordance with our internal quality control program. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication. All Neopoxy products come with a manufacturer’s product warranty active for one-year from date indicated on product label. This warranty exclusively covers Neopoxy products proven by the purchaser to be defective, up to but not exceeding either the purchase price of the product or a full replacement of the product. Neopoxy’s warranty does not cover defects that arise from the contractor’s improper storage, transportation, mixing, application, and/or workmanship. Our recommendations should not be taken as inducements to infringe any patent or violate any law, safety code, or insurance regulation.

THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL NEOPOXY BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS.